


STEP UP TO THE LUXURY OF OUR PRIVÉ COLLECTION




GRANO 1307

9" x 60" x 7.5"mm with a 22 mil wear layer




PLATANO 1405

9" x 60" x 7.5"mm with a 22 mil wear layer




SCURO 1461

9" x 60" x 7.5"mm with a 22 mil wear layer



PULITO 1518

9" x 60" x 7.5"mm with a 22 mil wear layer



INVERNO 8050

9" x 60" x 7.5"mm with a 22 mil wear layer

- **EMBOSSED IN REGISTER TEXTURE**
- **WIDE BEVEL**
- **LARGER AND THICKER PLANK**
- **MATTE FINISH**

SPECIFICATIONS



PRODUCT SPECIFICATION	STANDARD	7.5 mm. 12 MIL SPC Click	7.5 mm. 22 MIL SPC Click
Total Thickness	ISO 24337	7.50 mm with pad	7.50 mm with pad
Thickness of Wear Layer		0,275 mm(12 MIL)	0,55 mm(22 MIL)
Total Weight	EN ISO 23997	10.710 kg/m ²	10.710 kg/m ²
Usage Classification	EN 16511	Class 23	Class 23 / Class 34
Plank Size	ISO 24337	Click : 9"x60"	Click : 9"x60"
Packaging Per Carton: Planks		Click: 9"x60"- 15 SqFT/box - 5 pcs.	Click: 9"x60"- 15 SqFT/box - 5 pcs.
Underlayment optionally IXPE		+ 1.5mm IXPE Underlay	+ 1.5mm IXPE Underlay
Surface treatment (UV)		Yes	Yes
Beveled Edges		Yes - Wide Bevel	Yes - Wide Bevel
Dimensional Stability	EN-ISO 23999	≤0,15%	≤0,15%
Reaction to Fire	EN 13501-1	Class 1	Class 1
Residual Indentation	ISO 24343-1	≤ 0,05 mm	≤ 0,05 mm
Furniture Leg	EN 424	No damage	No damage
Castor Chair	ISO 4918 - EN 425	No change	No change
Locking Strength	ISO 24334	Longitudinal joint: 3.4 kN/m, Trans joint 3.6 kN/m	Longitudinal joint: 3.4 kN/m, Trans joint 3.6 kN/m
Impact Sound Reduction with 1mm IXPE Underlay	EN ISO 717-2	21 dB	21 dB
Light Fastness	EN ISO 105-B02	6 -7	6 -7
Resistance to Staining	EN 438-2	Groups 1 - 3: grade 5	Groups 1 - 3: grade 5
Micro Scratch Resistance	EN 16094	MSR-A2	MSR-A2
Impact Resistance	EN 13329 Annex F	> 1800 mm	> 1800 mm
Abrasion Resistance	EN 13329 Annex E	≥ 4000 cycles	≥ 4000 cycles
Thermal Resistance	EN 12664	0,0177 m ² K/W	0,0177 m ² K/W
Slip Resistance	DIN 51130 EN 13893	R9 μ ≥ 0,30 DS	R9 μ ≥ 0,30 DS
Static Electrical Propensity	EN 1815	≤2kV	≤2kV
Formaldehyde	EN 717-1:2014	E1 (Formaldehyde Free)	E1 (Formaldehyde Free)
STC Sound Testing	ASTM 492-09	STC 60	STC 60
IIC Sound Testing	ASTM E 989-18	IIC 62	IIC 62
Pentachlorophenol (PCP)	CP 491510-01	PCP Free	PCP Free
Floor Heating System	Yes suitable, see separate installation instructions.	Max. 29° C	Max. 29° C
FloorScore	Indoor Air Quality Certified to SCS-EC10.3-2014 v4.0	SCS-FS-05915	SCS-FS-05915

Surface Texture

Embossed in Register (EIR)

Embossed in Register (EIR)



TS EN 14041



Phthalate Free



12 Year Limited Service



europine.com



30-YEAR RESIDENTIAL / 7-YEAR COMMERCIAL
WARRANTY

sales@europine.com